

# Tek-cril 196 VV60



## RESINA ACRILICA

Resina acrílica con grupos hidroxilo libres para curado con isocianatos.

## ACRYLIC RESIN

Acrylic resin with free hydroxyl groups for curing reaction with isocyanates

## COMPOSICION

Copolímero conteniendo grupos hidroxilo libres, aprox. 1,5% sobre resina tal cual o 2,5% s/solidos

## COMPOSITION

Copolymer containing free hydroxyl groups, approx. 1,5% on resin as such or 2,5% on solids

### - Composición del solvente

Aromatico Pesado 100%

### - Solvent composition

Aromatic solvent 100%

## SPECIFICATIONS/ ESPECIFICACIONES

Property / Propiedad	Value/Valor	Units/ Unidad	Method/Metodo ( * )	Norm Reference/ Norma Referente
Viscosity / Viscosidad	X-Z2	Gardner	D-055	ASTM D1545
Non volatiles / Solidos	60 ± 1	%	D-116/1	ASTM D1644
Colour / Color	max 2	Hellige	D-019	ASTM D1545-NI1109
Acid number / Indice Acidez	max 5	Volume	D-149	ASTM D 465/1639
Appearance / Apariencia	Clear/Transparent Clara/ Transparente	Visual	D-020	-----
Density / Densidad	1,01 ± 0.02	Kg / dm <sup>3</sup>	D-022	DIN 53217
Flash Point/ Punto inflamacion	26°C	°C	D-547	DIN 53213

( \* ) Methods of determination (available on request)/ Metodos de determinación (disponibles a pedido)

## SOLUBILIDAD

Aguarras	incompatible
Xileno	completa
Acetato de Butilo	completa
Metiletilcetona	completa
Butanol	limitada

## SOLUBILITY

Mineral Spirit	not dilutable
Xylene	complete
Butyl Acetate	complete
MEK	complete
Butanol	limited

## PROPIEDADES PRINCIPALES

Curada con isocianatos confiere alta resistencia química, dureza y adhesión. Excelente brillo.

## MAIN PROPERTIES

Cured with isocyanates confer high chemical resistance, hardness, adhesion and excellent gloss.

## APLICACIONES

Para retocar sistemas bicapa automotores. Pinturas con excelentes propiedades de curado a temperatura ambiente. Lacas industriales con buena adhesión sobre sustratos difíciles (plásticos).

## APPLICATIONS

For repainting two coat metallic car system. Air drying paints with excellent film properties. Industrial lacquers with good adhesion on difficult substrates (paints for plastics parts).

## FORMAS DE USO

TK 196 / Desmodur N 75 (tal cual) 80 / 20

## USES

TK 196 / Desmodur N 75 (as such) 80 / 20

## FORMAS DE ENTREGA

Al 60% en Aromatico Pesado en tambores de hierro con 180 kg netos.

## SUPPLIED FORMS

60% in Aromatic solvent, in drums containing 180 kg net.

Nota: los datos arriba consignados se han obtenido de ensayos realizados en nuestro laboratorio. Los mismos son altamente confiables, pero declinamos toda responsabilidad respecto al uso que se haga de ellos.

Note: The above mentioned indications are based on carefully made tests in our laboratory. However, no liability can be assumed in the event of any errors. Tek-cril 196 VV60 is not found in the value listed above.