

# Tek-wax 093 WV25



## DISPERSION DE CERA

Dispersión de cera de polietileno

## WAX DISPERSION

Polyethylene wax dispersion

### COMPOSICION

Cera polietileno/Alkyd Largo 40 / 60  
(expresado sobre sólidos)  
Aditivos Metil Etil Cetoxima 1% (sobre fla total)

### - Composición del solvente

Aguarras 60%  
Aromatico pesado 40%

### COMPOSITION

Polyethylene wax/Long Oil Alkyd 40 / 60  
( based on solids)  
Aditives Methyl Ethyl Ketoxime 1% (on formula)

### - Solvent composition

White Spirit 60%  
Aromatic Solvent 40%

## SPECIFICATIONS/ ESPECIFICACIONES

Property / Propiedad	Value/Valor	Units/ Unidad	Method/Metodo ( * )	Norm Reference/ Norma Referente
CF4 25°C Viscosity / Viscosid	20 -30	seg	D-056	
Non volatiles / Solidos	25± 2	%	D-116/4	ASTM D1644
Appearance / Apariencia	Milky dispersion/Dispersión lechosa	Visual	D-020	-----
Density / Densidad	0,86 ± 0.02	Kg / dm <sup>3</sup>	D-022	DIN 53217
Flash Point/ Punto inflamacion	35	°C	D-547	DIN 53213

(\* ) Methods of determination (available on request)/ Metodos de determinación (disponibles a pedido)

### SOLUBILIDAD

Solventes alifáticos diluible  
Solventes aromáticos diluible  
Butanol limitada  
Esteres diluible

### SOLUBILITY

Aliphatic solvents dilutable  
Aromatic solvents dilutable  
Butanol limited  
Esters dilutable

### COMPATIBILIDAD

Presenta buena compatibilidad con resinas alquídicas medias y largas. Con Stand oil de Lino es limitada

### COMPATIBILITY

Good compatibility with long and medium oil alkyd resins, and reduced compatibility with Linseed Stand-Oil.

### PROPIEDADES PRINCIPALES

Excelente mateante para barnices, esmaltes e impregnantes tipo Cetol y Lasur. Confiere una superficie tersa y suave al tacto. Confiere resistencia a la abrasión y repelencia al agua.

### MAIN PROPERTIES

Excellent matting for varnishes, enamels and stains ( type Cetol or Lasur).  
It gives a smooth and soft surface to the touch.  
Confers abrasion resistance and water repellency

### APLICACIONES

En esmaltes satinados de secado al aire de alta calidad. No produce resquebrajamiento del film luego de envejecido.

### APPLICATIONS

In the formulation of air drying enamels and varnishes of high quality and low gloss or matt surfaces, achieving good crazing resistance after outdoor exposures.

### FORMA DE USO

Se sugiere usar de 2 a 5% de sólidos de cera sobre el producto

### USES

Recommended dosage, 2 to 5% of wax solids on total formulation.

### FORMAS DE ENTREGA

Al 25% en Aguarras/Arope 60/40 en tambores de hierro con 160 kg netos.

### SUPPLIED FORMS

25% in White Spirit/Aromatic 60/40, in drums containing 160 kg net.

Nota: los datos arriba consignados se han obtenido de ensayos realizados en nuestro laboratorio. Los mismos son altamente confiables, pero declinamos toda responsabilidad respecto al uso que se haga de ellos.

Note: The above mentioned indications are based on carefully made tests in our laboratory. However, no liability can be assumed in the event of any inaccuracy or incompleteness being found in the value listed above.